

LGLT 2

SKF Low Temperature, Extremely High Speed Bearing Grease

SKF LGLT 2 is a fully synthetic oil based grease using lithium soap. Its unique thickener technology and low viscosity oil (PAO) provide excellent lubrication performances at low temperatures $-50\text{ }^{\circ}\text{C}$ ($-60\text{ }^{\circ}\text{F}$) and extremely high speeds (n_{d_m} values of $1,6 \times 10^6$ can be reached).

- Low friction torque
- Quiet running
- Extremely good oxidation stability and resistance to water

Typical applications:

- Textile spinning spindles
- Machine tool spindles
- Instruments and control equipment
- Small electric motors used in medical and dental equipment
- In-line skates
- Printing cylinders
- Robots



Technical data

Designation	LGLT 2/(pack size)	
DIN 51825 code	K2G-50	
NLGI consistency class	2	
Soap type	Lithium	
Colour	Beige	
Base oil type	Synthetic (PAO)	
Operating temperature range	-50 to $+110\text{ }^{\circ}\text{C}$ (-60 to $+230\text{ }^{\circ}\text{F}$)	
Dropping point DIN ISO 2176	$>180\text{ }^{\circ}\text{C}$ ($>355\text{ }^{\circ}\text{F}$)	
Base oil viscosity	$40\text{ }^{\circ}\text{C}$, mm^2/s	18
	$100\text{ }^{\circ}\text{C}$, mm^2/s	4,5
Penetration DIN ISO 2137	60 strokes, 10^{-1} mm	265–295
	100 000 strokes, 10^{-1} mm	+50 max.
Mechanical stability	Roll stability,	380 max.
	50 hrs at $80\text{ }^{\circ}\text{C}$, 10^{-1} mm	
Corrosion protection	Emcor: – standard ISO 11007	0–1
Water resistance	DIN 51 807/1,	
	3 hrs at $90\text{ }^{\circ}\text{C}$	1 max.
Oil separation	DIN 51 817,	
	7 days at $40\text{ }^{\circ}\text{C}$, static, %	<4
Copper corrosion	DIN 51 811, $110\text{ }^{\circ}\text{C}$	1 max. at $100\text{ }^{\circ}\text{C}$ ($210\text{ }^{\circ}\text{F}$)
	Rolling bearing grease life	
ROF test	>1 000,	
L_{50} life at 10 000 r/min., hrs	20 000 r/min. at $100\text{ }^{\circ}\text{C}$ ($210\text{ }^{\circ}\text{F}$)	
EP performance	4–ball test,	2 000 min.
	welding load DIN 51350/4, N	
Available pack sizes	180 g tube	
	0.9, 25, 170 kg	